


K08-E

F-Slide



Ordering dimensions in **blue**

| Surface roughness | R_{tmax} | R_a |
|-------------------------|------------------|------------------|
| Sliding surface | $\leq 2 \mu m$ | $0,05-0,2 \mu m$ |
| Bottom of groove | $\leq 6,3 \mu m$ | $\leq 1,6 \mu m$ |
| Groove face | $\leq 15 \mu m$ | $\leq 3 \mu m$ |

Bearing area: 50–95% and a cutting depth of 0,5 R_z based on $C_{ref} = 0\%$

| Standard dimensions | | | | | | | Maximal radial extrusion gap | | | |
|---------------------|--------------|----------|-------|-----|------|-------|------------------------------|---------|---------|---------|
| D | H9 | d | L | R | c | OD | s^* | | | |
| over | | incl. | + 0,2 | | | | 100 bar | 200 bar | 400 bar | 600 bar |
| mm | | | | | | | mm | | | |
| 10 | 15 | D - 4,9 | 2,2 | 0,4 | 2,5 | 1,78 | 0,30 | 0,20 | 0,15 | 0,05 |
| 15 | 40 | D - 7,5 | 3,2 | 0,6 | 3,5 | 2,62 | 0,40 | 0,25 | 0,15 | 0,05 |
| 40 | 80 | D - 11 | 4,2 | 1,0 | 4,5 | 3,53 | 0,40 | 0,25 | 0,20 | 0,10 |
| 80 | 133 | D - 15,5 | 6,3 | 1,3 | 5,0 | 5,33 | 0,50 | 0,30 | 0,20 | 0,10 |
| 133 | 330 | D - 21 | 8,1 | 1,8 | 6,0 | 7,00 | 0,60 | 0,35 | 0,25 | 0,15 |
| 330 | 670 | D - 24,5 | 8,1 | 1,8 | 8,0 | 7,00 | 0,60 | 0,35 | 0,25 | 0,15 |
| 670 | 1 000 | D - 28 | 9,5 | 2,5 | 10,0 | 8,40 | 0,70 | 0,50 | 0,30 | 0,20 |
| 1 000 | 3 000 | D - 38 | 13,8 | 3,0 | 12,0 | 12,00 | 1,00 | 0,70 | 0,60 | 0,30 |

* The extrusion gap referred to is valid up to 80 °C and valid for the side opposite to the pressure side; higher temperatures require lower values.

Ordering example

Profile
D x d x L [mm]
Sealing material / Energizer

F-Slide K08-E
100 x 84,9 x 6,3
SKF Ecoflon 3 / NBR70

Operating parameters

| Material Seal | Energiizer | Temperature | | Speed ¹⁾ | Pressure ²⁾ |
|-----------------|------------|-------------|------|---------------------|------------------------|
| | | from | to | max | max |
| | | °C | | m/s | bar (MPa) |
| – | | | | | |
| ■ SKF Ecoflon 2 | FKM75 | –20 | +200 | 10 | 600 (60) |
| ■ SKF Ecoflon 3 | | | | | |
| ■ SKF Ecoflon 4 | NBR70 | –30 | +100 | | |

IMPORTANT NOTE: The stated operating conditions represent general indications. It is recommended not to use all maximum values simultaneously.

¹⁾ Surface speed limit values are valid only in the presence of a lubrication film.

²⁾ Pressure ratings depend on the size of the extrusion gap.