


PISTON SEAL SEAL HOUSING

K21-P



Ordering dimensions in **blue**

Surface roughness	$R_{t\max}$	R_a
Sliding surface	$\leq 2,5 \mu\text{m}$	$0,05\text{--}0,2 \mu\text{m}$
Bottom of groove	$\leq 6,3 \mu\text{m}$	$\leq 1,6 \mu\text{m}$
Groove face	$\leq 15 \mu\text{m}$	$\leq 3 \mu\text{m}$

Bearing area: 50–95% and a cutting depth of $0,5 R_z$ based on $C_{ref} = 0\%$

D H9 over	d h10 incl.	L $+0,2$	$R_{t\max}$	C	Maximal radial extrusion gap				
					20 bar	100 bar	200 bar	400 bar	
mm							mm		
13	25	D - 8	6,0	0,4	3,5	0,33	0,18	0,11	0,05
25	50	D - 10	7,0	0,4	4,0	0,37	0,22	0,16	0,10
50	75	D - 12	8,0	0,4	4,5	0,42	0,27	0,20	0,14
75	150	D - 15	10,0	0,4	5,0	0,46	0,31	0,25	0,19
150	300	D - 20	12,0	0,4	6,0	0,54	0,39	0,32	0,26
300	500	D - 25	18,0	0,4	8,5	0,61	0,46	0,39	0,33
500	600	D - 30	20,0	0,4	10,0	0,67	0,52	0,45	0,39

* Extrusion gap values shown above are valid for a temperature of 70 °C, higher temperatures require lower values.

Ordering example

Profile

D x d x L [mm]

Sealing material / Energizer

Piston seal K21-P

100 x 85 x 10

ECOPUR / NBR 70

Operating parameters

Material Seal	Energizer	Temperature		Speed ¹⁾ max	Pressure ²⁾ max
		from	to		
-		°C		m/s	bar (MPa)
■ ECOPUR		-30			
■ H-ECOPUR	NBR 70	-20	+100	0,5	
■ S-ECOPUR				0,7	400 (40)
■ T-ECOPUR	MVQ70	-50	+110	0,5	

IMPORTANT NOTE: The stated operating conditions represent general indications. It is recommended not to use all maximum values simultaneously.

¹⁾ Surface speed limit values are valid only in the presence of a lubrication film.

²⁾ Pressure ratings depend on the size of the extrusion gap.